



Determination of SILVERSTAR glazing characteristics

Version information:
Program 3.10
Database 3.56
Output format 3.21

The following characteristics are calculated with the program SILVERSTAR glaCE.

Project: Velux Lydglas

Company: Interglas

Employee: LA


Customer:

Product:

Date: 21.04.2021

Glazing:

Window tilt angle: 90 °



Comments:

Calculated glazing characteristics:

Thermal transmittance Ug:	1.9992 W/m²K	EN 673:2011
Total solar energy transmittance (solar factor g):	62.168 %	EN 410:2011
Light transmittance:	81.045 %	
Light reflectance (outside):	11.799 %	
Light reflectance (inside):	11.498 %	
Light absorptance:	7.155 %	
Solar direct transmittance:	54.805 %	
Solar direct reflectance (outside):	23.694 %	
Solar direct absorptance:	21.501 %	
Secondary internal heat transfer factor:	7.363 %	
UV-Transmittance:	28.765 %	
UV-Reflectance:	15.895 %	
UV-Absorptance:	55.340 %	
General colour rendering index (transmission):	97.207	
Selectivity (light transmittance / solar factor g):	1.3036	
Shading coefficient (solar factor g / 0.87):	71.458 %	
Shading coefficient (solar factor g / 0.8):	77.710 %	

CE

The values given are only indicative and subject to change without notice.
They do not represent any guarantee for the performance of the glazing
Calculations are performed according to the European standards EN 410:2011 and EN 673:2011.